

TEST REPORT


Issue Date: 2020-08-18
 Test Date(s): 2020-08-04 - 2020-08-14
 Applicant: Ekologix Australia Pty Ltd
 Address: Unit 1, 20-26 Sabre Drive, Port Melbourne, Victoria, Australia 3207

Intertek Report No. : 200804001SHF-001

Test Type : Performance test, samples provided by the applicant.

Document Control Number: LFT-APAC-SHF-OP-10k(May 1,2020)

© 2020 INTERTEK



Product Information

Product Name	Designer Series, Designer Series Edge Boards Flame Fighter BAL29 WPC Co-Extrusion Decking	Brand	Ekodeck
Sample Description	Good Condition	Sample Amount	11 PCS
		Received Date	2020-08-03
Sample ID	Model	Specification	
S200804001SHF.001	BR6	137*23mm	

Test Items, Method and Results:

Test Item: The body voltage (Static electrical propensity)
 Test Method: EN 1815:2016, Method A - Test procedure in laboratory conditions
 Conditioning: Condition the test specimens at (23±2)°C and (25±2)% relative humidity for at least 7 days
 Test Condition:
 Temperature: 23±2 °C
 Relative humidity: 25±2 %
 Substructure: A earthed metal base plate
 Material of the sandal sole: Rubber

Test Result: 0.6 kV

Report Authorized


 Name: Flora Fan
 Title: Reviewer


 Name: Mason Wang
 Title: Project Engineer

